AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions and listings of claims in the application:

- 1. (Previously presented) A radioactive microsphere comprising not less than 99% by weight of a crystal of an oxide of yttrium which contains 47% by weight or more of radioactive yttrium, and the balance of inevitable impurities, wherein the microsphere is in the shape of a sphere.
- 2. (Original) The radioactive microsphere according to claim 1, wherein the oxide crystal consists essentially of Y_2O_3 .
- 3. (Original) The radioactive microsphere according to claim 1, wherein the oxide crystal consists essentially of YPO₄, or a mixture of Y₂O₃ and YPO₄.
- 4. (Original) The radioactive microsphere according to claim 1, wherein the microsphere has a diameter of 1 to 100 μm .
- 5. (Original) The radioactive microsphere according to claim 1, wherein the microsphere has a diameter of 2 to 30 μ m.
- 6. (Previously presented) The radioactive microsphere according to any one of claims 1 to 5, wherein the microsphere is coated with a film comprising at least one of the compounds selected from the group consisting of silica (SiO₂), titania (TiO₂), alumina (Al₂O₃), iron (III) oxide (Fe₂O₃), silicon nitride (Si₂N₃), SiN, Si₃N₄), aluminum nitride (AlN), titanium nitride (TiN), iron nitride (Fe₂N, Fe₄N), silicon carbide (SiC) and titanium carbide (TiC).
- 7. (Original) The radioactive microsphere according to claim 6, wherein the film has a thickness of 0.01 to 5 μ m.

- 8. (Currently amended) A method of producing a radioactive microsphere, the method comprising preparing a microsphere having not less than 99% by weight of a crystal of an oxide of yttrium which contains 47% by weight or more of non-radioactive yttrium, and the balance of inevitable impurities through melting of an oxide powder containing yttrium as a starting material by passing the starting material through a high frequency induction thermal plasma wherein the microsphere is formed into a sphere, followed by irradiating with an effective dosage of slow neutrons to turn non-radioactive yttrium into a radioactive element.
 - 9. (Cancelled)
- 10. (Previously presented) The method according to claim 8, further comprising coating the microsphere with a film after preparing the microsphere and before irradiating with an effective dosage of slow neutrons, the film comprising at least one of the compounds selected from silica (SiO₂), titania (TiO₂), alumina (Al₂O₃), iron (III) oxide (Fe₂O₃), silicon nitride (Si₂N₃, SiN, Si₃N₄), aluminum nitride (AlN), titanium nitride (TiN), iron nitride (Fe₂N, Fe₄N), silicon carbide (SiC) and titanium carbide (TiC).
- 11. (Previously presented) The method according to claim 8, wherein the oxide crystal further contains an amount of phosphorus, and the method further comprises heating the microsphere in an oxidizing atmosphere after preparing the microsphere and before irradiating with an effective dosage of slow neutrons.
- 12. (Previously presented) The method according to claim 11, further comprising coating the microsphere with a film after heating in the oxidizing atmosphere and before irradiating with an effective dosage of slow neutrons, the film comprising at least one of the compounds selected from silica (SiO₂), titania (TiO₂), alumina (Al₂O₃),

iron (III) oxide (Fe₂O₃), silicon nitride (Si₂N₃, SiN, Si₃N₄), aluminum nitride (AlN), titanium nitride (TiN), iron nitride (Fe₂N, Fe₄N), silicon carbide (SiC) and titanium carbide (TiC).

- 13. (Cancelled).
- 14. (Currently amended) The method according to claim 8, wherein the starting material is an oxide powder containing yttrium, or yttrium and phosphorous.
- 15. (Currently amended) A combination of kit comprising a catheter and a microsphere for use with the catheter, comprising a catheter and at least one microsphere having not less than 99% by weight of a crystal of an oxide of yttrium which contains 47% by weight or more of radioactive yttrium, and the balance of inevitable impurities, wherein the microsphere is in the shape of a sphere.